



中国认可
国际互认
检测
TESTING
CNAS L0699



TEST REPORT

CEPRI-EET02-2023-0058 (E)

Client: Xi 'an Tiangong Electric Co.,Ltd

Object: Metal Oxide Varistor

Type: $\Phi 60\text{mm} \times 24\text{mm}$

Test Category: Characteristics test

**POWER INDUSTRY QUALITY INSPECTION AND TEST
CENTER FOR ELECTRIC EQUIPMENT**



NOTICE

1. This report will enter into effect with seals of test center.
2. This report is legally made available accompany with compiled, checked, verified and approved signatures.
3. Alter the report is invalid.
4. This report only takes responsibility to the test object.
5. Part of copy is invalid.
6. Any objections in the report should be posed within 15 days once the report is received.
7. The inspection and testing management system of China Electric Power Research Institute includes the following institutes:

National Wind Power Integration Research and Test Center

☆ **Power Industry Quality Inspection and Test Center for Electric Equipment**

Power Industry Quality Inspection & Test Center for Electric Power Equipment and Instruments

Power Industry Quality Inspection & Test Center for Electrical Material and Components

Power Industry Quality Inspection & Test Center for Automation Equipment

Power Industry Quality Inspection & Test Center for Communication Equipment

Power Industry Quality Inspection & Test Center for Concrete Power and Communication Poles

Power System Electromagnetic Compatibility and Electromagnetic Environmental Research and Monitoring Center

Address: NO.143, Luoyu Road, Hongshan District, Wuhan, Hubei Province, 430074.


Fax: 86-27-5937-8488 Service line:86-27-59258069 Supervision hotline: 86-10-82813498

E-mail: eetc@epri.sgcc.com.cn

Website: <http://www.epri.sgcc.com.cn>

Catalogue

| | |
|---|----|
| 1.Catalogue..... | 1 |
| 2.Signature Page..... | 2 |
| 3.Test Results..... | 3 |
| 4.Content..... | 5 |
| 5.Appendix A Sample instruction..... | 9 |
| 6.Appendix B Main test device..... | 9 |
| 7.Appendix Che Typical Test Waveform..... | 10 |
| 8.Appendix D Photos of the arrester..... | 12 |





| | | | |
|--|--|--------------|--|
| Test Report | Power Industry Quality Inspection and Test Center for Electric Equipment 检测报告 专用章 | | CEPRI-EETC02-2023-0058(E) Total 12 Page 2 |
| Client | Xi 'an Tiangong Electric Co.,Ltd | Manufacturer | Xi 'an Tiangong Electric Co.,Ltd |
| Object | Metal Oxide Varistor | Type | Φ60mm×24mm |
| Sampling procedure | By the client delivery | Serial No. | 19 resistors (301~319) |
| Test Category | Characteristics test | Date | 2023.02.13~2023.03.31 |
| Requirements | 1. GB/T 11032-2020 Metal-oxide surge arresters without gaps for a.c. systems 2. IEC 60099-4 Edition 3.0 (2014-06) Metal-oxide surge arresters without gaps for a.c. systems | | |
| Conclusion | The metal oxide Varistor(Φ60mm×24mm) has passed the type test specified in GB/T 11032-2020 and IEC 60099-4 Edition 3.0 (2014-06). | | |
| Note | Note :See appendix A for sample instruction. | | |
| Tested by: 梁菊霞  陈立  | | | |
| Checked by: 王陆璐  Verified by: 左中秋  | | | |
| Approved by: 王保山  Date of issue: 2023-04-12 | | | |



Test Results

| No. | Item | Requirements | Results | Evaluation | |
|-----|---|--|--|----------------------------|-----------|
| 1 | Residual voltage test | Lightning impulse | $\leq 8.69 \pm 0.5 kV_p$ | $8.60 kV_p \sim 8.69 kV_p$ | Data only |
| | | Switching impulse | Data only | See the text for details | |
| | | Steep current impulse | Data only | See the text for details | |
| 2 | High current impulse withstand test | 4/10 μ s、 100 kA 、 2times | 100.0kA~104.0kA | Pass | |
| 3 | Repetitive charge transfer rating withstand test | $Q_{rs} = 2C$ by 2ms rectangular current for 20 times. | 2.224 C ~2.405C | Pass | |
| 4 | Test to verify long term stability under continuous operating voltage | Charge ability 85%, 115 $^{\circ}$ C, 1000h. | $P_{max} \leq 1.3P_{min}$ $P_{all,max} \leq 1.1P_{start}$ | Pass | |

(No content in this page below)



Content:

1 Residual voltage test

1.1 Lightning impulse residual voltage test

| Samples | | | | 301 | 302 | 303 |
|-----------------|--------------------|-----------------|-----------------|---------------------|------|------|
| Resistor | U_{3mAAC} | Measured value | kV | 3.86 | 3.84 | 3.84 |
| | | Specified value | kV _p | ≥ 3.66 | | |
| | 8/20 μ s, 5kA | | kV _p | 8.22 | 8.19 | 8.23 |
| | 8/20 μ s, 10kA | | kV _p | 8.69 | 8.60 | 8.62 |
| | 8/20 μ s, 20kA | | kV _p | 9.48 | 9.36 | 9.38 |
| Specified value | | | kV _p | $\leq 8.69 \pm 0.5$ | | |

Note 1: Shunt 0.025 V/A, divider $K_d=206.8$

Note 2: According to the determined residual pressure, draw the residual voltage and current curve, in the curve corresponding to the nominal discharge current read residual voltage, defined as the lightning protection lightning protection level.

1.2 Switching impulse residual voltage test

| Samples | | | | 301 | 302 | 303 |
|----------|---------------------------|----|-----------------|------|------|------|
| Resistor | U_{3mAAC} | kV | 3.86 | 3.84 | 3.84 | |
| | Residual voltage at 500A | | kV _p | 7.16 | 7.11 | 7.11 |
| | Residual voltage at 1000A | | kV _p | 7.28 | 7.24 | 7.28 |
| | Residual voltage at 2000A | | kV _p | 7.69 | 7.65 | 7.65 |

Note: Shunt 0.025 V/A, divider $K_d=206.8$

1.3 Steep current impulse residual voltage test

| Samples | | | | 301 | 302 | 303 |
|----------|--------------------|----|-----------------|------|------|------|
| Resistor | U_{3mAAC} | kV | 3.86 | 3.84 | 3.84 | |
| | 8/20 μ s, 10kA | | kV _p | 9.45 | 9.39 | 9.39 |

Note1: Shunt 0.0267 V/A, divider $K_d=59.8$.

Note 2: If U_{res2}/U_{res1} is less than 2%, there is no need to correct Inductive effect.

Data only. Test waveform is shown in figure C.1 ~ figure C.3.

(No content in this page below)



质量
报
章

| | | |
|--------------------|---|--|
| Test Report | Power Industry Quality Inspection and Test Center for Electric Equipment | CEPRI-EETC02-2023-0058(E) Total 12 Page 5 |
|--------------------|---|--|

2 High current impulse withstand test

Environment temperature: 17.0°C humidity: 53%

| Samples | | 304 | 305 | 306 | Specified value |
|----------------------------------|-------------------------------------|-------|-------|-------|---|
| U _{1mADC} (Positive +) | kV | 5.13 | 5.07 | 5.08 | / |
| U _{1mADC} (Negative -) | kV | 5.12 | 5.09 | 5.09 | / |
| 8/20μs U _{10kAp} before | kV _p | 8.54 | 8.52 | 8.51 | / |
| 1 st impulse | kA | 104.0 | 104.0 | 101.2 | 100kA, The interval should allow the samples to cool to ambient temperature |
| 2 nd impulse | | 100.0 | 101.2 | 100.0 | |
| U _{1mADC} (Positive +) | kV | 5.13 | 5.00 | 5.08 | / |
| Change rate (Positive +) | % | 0 | -1.38 | 0 | / |
| U _{1mADC} (Negative -) | kV | 5.06 | 5.02 | 5.05 | / |
| Change rate (Negative -) | % | -1.17 | -1.38 | -0.79 | / |
| Visual inspection | No puncture, flashover or cracking. | | | | No puncture, flashover or cracking. |

Note: Shunt 0.001V/A.

Fulfilled the requirements. Test waveform is shown in figure C.4.

(No content in this page below)



3 Repetitive charge transfer rating withstand test

Environment temperature: 13.0°C humidity:72%

| Samples | | 310 | 311 | 312 | 313 | 314 | 315 | 316 | 317 | 318 | 319 |
|---------------------|-------------------------------|---|-------|-------|-------|-------|-------|-------|-------|-------|-------|
| Before test | U _{3mAAC} , kV | 3.75 | 3.75 | 3.79 | 3.79 | 3.76 | 3.78 | 3.79 | 3.78 | 3.77 | 3.76 |
| | 8/20μsU _{10kA} , kV | 8.16 | 8.17 | 8.24 | 8.29 | 8.23 | 8.24 | 8.26 | 8.25 | 8.24 | 8.23 |
| Q _{rs} , C | | Q _{rs} (Claimed repetitive charge transfer rating) × 1.1=2.2 | | | | | | | | | |
| 1 st | Q _{rs} , C | 2.253 | 2.376 | 2.405 | 2.295 | 2.369 | 2.381 | 2.405 | 2.251 | 2.257 | 2.334 |
| 2 nd | Q _{rs} , C | 2.271 | 2.345 | 2.357 | 2.244 | 2.355 | 2.336 | 2.357 | 2.233 | 2.225 | 2.314 |
| 3 rd | Q _{rs} , C | 2.315 | 2.385 | 2.404 | 2.306 | 2.378 | 2.371 | 2.404 | 2.262 | 2.251 | 2.349 |
| 4 th | Q _{rs} , C | 2.295 | 2.348 | 2.344 | 2.243 | 2.335 | 2.322 | 2.344 | 2.224 | 2.233 | 2.315 |
| 5 th | Q _{rs} , C | 2.244 | 2.353 | 2.342 | 2.257 | 2.334 | 2.303 | 2.342 | 2.235 | 2.262 | 2.367 |
| 6 th | Q _{rs} , C | 2.306 | 2.350 | 2.277 | 2.225 | 2.314 | 2.269 | 2.277 | 2.251 | 2.224 | 2.328 |
| 7 th | Q _{rs} , C | 2.243 | 2.356 | 2.358 | 2.251 | 2.349 | 2.336 | 2.244 | 2.385 | 2.357 | 2.355 |
| 8 th | Q _{rs} , C | 2.257 | 2.321 | 2.324 | 2.233 | 2.315 | 2.316 | 2.306 | 2.348 | 2.404 | 2.378 |
| 9 th | Q _{rs} , C | 2.225 | 2.352 | 2.368 | 2.262 | 2.367 | 2.308 | 2.243 | 2.353 | 2.344 | 2.335 |
| 10 th | Q _{rs} , C | 2.251 | 2.405 | 2.356 | 2.224 | 2.328 | 2.302 | 2.257 | 2.350 | 2.342 | 2.334 |
| 11 th | Q _{rs} , C | 2.233 | 2.357 | 2.334 | 2.295 | 2.369 | 2.381 | 2.225 | 2.356 | 2.277 | 2.314 |
| 12 th | Q _{rs} , C | 2.262 | 2.404 | 2.314 | 2.334 | 2.355 | 2.336 | 2.251 | 2.321 | 2.358 | 2.349 |
| 13 th | Q _{rs} , C | 2.224 | 2.344 | 2.349 | 2.314 | 2.378 | 2.371 | 2.233 | 2.364 | 2.324 | 2.315 |
| 14 th | Q _{rs} , C | 2.295 | 2.342 | 2.315 | 2.349 | 2.334 | 2.322 | 2.262 | 2.319 | 2.368 | 2.367 |
| 15 th | Q _{rs} , C | 2.334 | 2.277 | 2.367 | 2.315 | 2.314 | 2.303 | 2.224 | 2.385 | 2.339 | 2.328 |
| 16 th | Q _{rs} , C | 2.314 | 2.358 | 2.334 | 2.367 | 2.349 | 2.269 | 2.244 | 2.348 | 2.357 | 2.355 |
| 17 th | Q _{rs} , C | 2.349 | 2.324 | 2.314 | 2.328 | 2.315 | 2.336 | 2.306 | 2.353 | 2.304 | 2.378 |
| 18 th | Q _{rs} , C | 2.315 | 2.368 | 2.349 | 2.334 | 2.367 | 2.316 | 2.243 | 2.35 | 2.340 | 2.335 |
| 19 th | Q _{rs} , C | 2.367 | 2.335 | 2.315 | 2.314 | 2.328 | 2.308 | 2.257 | 2.356 | 2.342 | 2.334 |
| 20 th | Q _{rs} , C | 2.338 | 2.328 | 2.367 | 2.349 | 2.334 | 2.287 | 2.225 | 2.321 | 2.277 | 2.314 |
| Test evaluation | U _{3mAAC} , kV | 3.80 | 3.80 | 3.86 | 3.86 | 3.82 | 3.86 | 3.85 | 3.86 | 3.84 | 3.82 |
| | Change rate, % | +1.33 | +1.33 | +1.85 | +1.85 | +1.60 | +2.12 | +1.58 | +2.12 | +1.86 | +1.60 |
| | 8/20μs U _{10kA} , kV | 8.21 | 8.28 | 8.32 | 8.34 | 8.32 | 8.31 | 8.32 | 8.34 | 8.32 | 8.30 |
| | Change rate, % | +0.61 | +1.35 | +0.97 | +0.60 | +1.09 | +0.85 | +0.72 | +1.09 | +0.97 | +0.85 |
| | One 8/20 current impulse, kA | 14.13kA (0.5kA/cm ² =0.5×3.14×(6.0/2) ² =14.13kA which is lower than 2 times I _n) | | | | | | | | | |
| | Visual inspection | All the samples have no puncture, flashover or cracking. | | | | | | | | | |

Note: Shunt 0.01V/A.

Fulfilled the requirements, the test waveforms were shown in fig C.5.



| | | | |
|--------------------|---|--|--|
| Test Report | Power Industry Quality Inspection and Test Center for Electric Equipment | CEPRI-EETC02-2023-0058(E) Total 12 Page 7 | |
|--------------------|---|--|--|

4 Test to verify long term stability under continuous operating voltage

| Samples | 307 | 308 | 309 |
|---|-------|-------|-------|
| U_{1mADC} , kV | 5.15 | 5.20 | 5.18 |
| U_{ct} , kV _{rms} | 3.31 | 3.31 | 3.31 |
| Charge rate,% | 90.1 | 90.0 | 90.4 |
| U_{3mAAC} , before test | 3.75 | 3.78 | 3.79 |
| U_{3mAAC} ,after test | 3.97 | 3.98 | 3.95 |
| Change rate, % | +5.34 | +5.30 | +4.23 |
| Power losses P_{start} , 3h, W | 2.404 | 2.111 | 2.864 |
| Power losses P_{100h} , W | 2.060 | 1.849 | 2.760 |
| Power losses P_{200h} , W | 1.989 | 1.817 | 2.196 |
| Power losses P_{300h} , W | 2.224 | 1.771 | 2.143 |
| Power losses P_{400h} , W | 1.979 | 1.959 | 2.060 |
| Power losses P_{500h} , W | 1.856 | 1.771 | 2.298 |
| Power losses P_{600h} , W | 2.064 | 1.681 | 2.046 |
| Power losses P_{700h} , W | 1.985 | 1.847 | 1.919 |
| Power losses P_{800h} , W | 2.072 | 1.777 | 2.128 |
| Power losses P_{900h} , W | 2.011 | 1.831 | 2.048 |
| Power losses P_{end} , 1000+8h,W | 2.090 | 1.782 | 2.136 |
| P_{min} , W | 1.846 | 1.681 | 1.919 |
| Any increase of power losses from P_{min} during the remaining test period, P_{max} | 2.090 | 1.847 | 2.136 |
| $P_{all.max}$, W | 2.404 | 2.111 | 2.864 |
| $P_{max} / 1.3P_{min}$ | 0.866 | 0.845 | 0.856 |
| $P_{all.max} / 1.1 P_{start}$ | 0.909 | 0.909 | 0.909 |

Because $P_{max} \leq 1.3P_{min}$, $P_{all.max} \leq 1.1P_{start}$, the samples fulfilled the requirements.

Note: The temperature of blocks: $115 \pm 4^\circ C$.

Fulfilled the requirements, the accelerated ageing curves were shown in fig 1.






Fig 1 The Accelerated ageing curve of samples

(No content in this page below)



Appendix A: Sample instruction

Sample instruction:

- 1) 19 resistors, number EETC02-23/01/20-0058-301~ EETC02-23/01/20-0058-319, short for 301~319 in report.

Appendix B: Main test device

| NO. | Device name | Device NO. | Measurement | Uncertainty /Accuracy | Calibration institution | Expiration date |
|-----|--|-------------|--|--|---|-----------------|
| 1 | impulse current generator | EETC02-0003 | 8/20 μs 40 kA 4/10 μs 130 kA | U _{rel} =0.015 k=2 | National center for high voltage measurement | 2023-06-23 |
| 2 | impulse current generator | EETC02-0005 | 8/20 μs 40 kA 30 kV 4/10 μs 2 kA 30 kV | U _{rel} =0.015 k=2 U _{rel} =0.018 k=2 | National center for high voltage measurement | 2023-06-29 |
| 3 | Steep current impulse generator | EETC02-0004 | 8/20 μs 40 kA 30 kV 30/80 μs 2 kA 30 kV | U _{rel} =0.015 k=2 U _{rel} =0.018 k=2 | National center for high voltage measurement | 2023-06-29 |
| 4 | DC reference voltage tester | EETC02-0049 | DC 0~9 kV | U _{rel} =0.008 k=2 | Hubei province meteorological metrological verification station | 2023-07-12 |
| 5 | Accelerated aging device for MO resistor | EETC02-0036 | 115℃ | U _{rel} =0.3℃k=2 | Hubei province meteorological metrological verification station | 2023-08-03 |
| | | | 0~10kV | U _{rel} =0.013 k=2 | National center for high voltage measurement | 2024-03-08 |

(No content in this page below)



Appendix C The typical test waveform




Fig C.1 Lightning impulse current and residual voltage waveform (sample 301, shunt 0.025V/A, divider $K_d=206.8$)




Fig C.2 Switching impulse current and residual voltage waveform (sample 301, shunt 0.025V/A, divider $K_d=206.8$)




Fig C.3 Steep impulse current and residual voltage waveform (sample 301, shunt 0.0267V/A, divider $K_d=59.8$)

质量
报
章






Fig C.4 Waveform of 304 conditioning test (first impulse)



Fig C.5 The 1st time of sample 310, Repetitive charge transfer withstand, 0.01V/A

(No content in this page below)



检测中心
告

Appendix D: Photos of the arrester



Fig D1: Outside view of MO resistor ($\Phi 60\text{mm} \times 24\text{mm}$)

111111

